

WESTERN PLASTICS

41995 BUSINESS PARK DRIVE TEMECULA, CA 92590

Telephone (951) 695-1983 Fax (951) 695-2004 Wats (800) 442-9727 E-Mail: western@wplastics.com

Web: www.wplastics.com

Dissipative Stretch Wrap Specifications

<u>Tensile</u>		<u>Stretch Film</u>				<u>Yield</u>			<u>Standard Sizes</u>	
<u>Ultimate</u>										
	mil	lbs	psi	%elong	lbs	psi	%elong	<u>Handwrap</u>		
MD	0.78	7.1	9100	680	1.2	1570	62	4 rolls per case		
TD	0.83	4.7	5680	1050	1.0	1200	18	17.5" 80 ga 1500' 36 cs/plt		
<u>2% Secant Modulus</u>										
	mil	psi								
MD	0.71	17690								
TD	0.80	18480								
<u>Spencer Impact</u>										
Avg 16.040 psi									<u>Machine Grade</u>	
									40 rolls per pallet	
<u>Tear</u>									20" 80 ga 5000'	
MD	371 g Stretches & Oblique Tears									
TD	585 g Stretches & Oblique Tears									
<u>Puncture - FED TEST 101C, Method 2065</u>										
	mil	lbs/force	elong							
Avg	0.85	4.1	2.4					Average Lead Time: 2 weeks		
<u>Static Decay - FED STD 101C, Method 4046</u>										
+ 5KV		Less than 2 seconds								
<u>Surface Resistivity - 10₁₁ ohm/square nom</u>										
ASTM D 257										

DISCLAIMER - SELLER MAKES NO WARRANTY, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE, except that the product shall conform to contracted specifications. Determination of the suitability of the product for the uses and applications contemplated by Buyer and others shall be the sole responsibility of Buyer. Buyer's exclusive remedy shall be for damages and no claim of any kind, whether as to product delivered or for non-delivery of product, and whether based on contract, breach of warranty, negligence or otherwise shall be greater in amount than the purchase price of the quantity of the product in respect of which damages are claimed. In no event shall Seller be liable for incidental or consequential damages, whether Buyer's claim is based on contract, breach of warranty, negligence or otherwise.